


ROPE 6x7 Covered



Minimum Breaking Force Factor
K = 0,332

Nominal Length Mass Factor
W = 0,345

Diameter	kg/100M	1770		1960		1570 (AISI)	
		kN	Kg	kN	Kg	kN	Kg
1,0	0,35	0,59	60	0,65	66	0,52	53
1,5	0,78	1,32	135	1,46	149	1,17	120
2,0	1,38	2,35	240	2,60	265	2,08	213
2,5	2,16	3,67	374	4,07	415	3,26	332
3,0	3,11	5,29	539	5,86	597	4,69	478
4,0	5,52	9,40	958	10,41	1.061	8,34	850
5,0	8,63	14,69	1.498	16,27	1.658	13,03	1.328
6,0	12,42	21,20	2.156	23,40	2.388	18,80	1.913
8,0	22,08	37,60	3.834	41,60	4.245	33,40	3.401
10,0	34,50	58,80	5.990	65,10	6.633	52,10	5.313
12,0	49,68	84,60	8.626	93,70	9.552	75,10	7.651
14,0	67,62	115,20	11.741	127,50	13.001	102,20	10.414
16,0	88,32	150,40	15.335	166,60	16.981	133,40	13.602